

## DEF600HT Heat Treated Fabric

### Description

Heat-treated E-glass fabric, with its organic sizing burned off, is used for high-temperature insulation, thermal barriers, and personal protective equipment like welding blankets, curtains, and fireproof materials. Offering excellent heat/flame resistance for industrial applications where smoke is a concern, such as furnace insulation, expansion joints, and gaskets

**Compliant with Mil Spec MIL-C20079H, Type 1, Class 9**



### Applications

- **Welding & Fire Protection** (Welding blankets, fire curtains, and firewalls to protect against sparks, heat, and flames)
- **Industrial Insulation** (Pipe & furnace insulation, thermal reflectors, and machinery covers due to its resistance to extreme heat (up to 550-700°C))
- **Protective Gear** (Personal protective equipment (PPE) like aprons, cuffs, and suits for workers in high-heat environments)
- **Expansion Joints** (Used in compensators and expansion joints in industrial systems)
- **Gaskets** (High-temperature gaskets for sealing applications.)
- **Thermal Covers** - Exhaust, Muffler, Turbo jackets etc.

### Benefits of Heat Treatment

- **Smoke-Free:** Removes organic sizing, preventing smoke during initial use.
- **Improved Performance:** Offers better abrasion resistance and direct flame resistance after treatment.
- **Versatility:** Can be further coated (e.g., with silicone or vermiculite) for enhanced properties like water resistance or chemical stability

### Technical Data

Technical Data				
1	Weave		Style HT2025A Plain	Testing Method
2	Yarn	Warp	EC9 430tex	ISO 4602
	Texturized	Weft	EC9 430tex	ISO 4602
3	Width		100 cm	DIN EN 1773
			150 cm	DIN EN 1773
4	Cloth Weight		600 g/m <sup>2</sup>	DIN EN 12127
5	Treatment		Caramelised (heat treated) and acrylic weave locked	-
6	Thickness		0.9mm	DIN EN ISO 5084
7	Thread Count	Warp	8 per cm	DIN EN 1049-2
		Weft	5.7 per cm	DIN EN 1049-2
8	Tensile Strength(min)	Warp	2250 N/5cm	EN ISO 13934-1
		Weft	1216 N/5cm	EN ISO 13934-1
9	Service Temperature		550°C	-

Revised 16/06/2026