

## Pizza Oven Castable

### How to use in the process of construction:

1. Preparing a mixer firstly, putting proper quantity castable into the mixer as per specific requests (note there are one small plastic bag in each package, unpack it and mix the powder together in mixer), after about 0.5-1 minute, add suitable quantity water (usually 6-7% by weight, and can be slightly adjusted according to the requirement of construction) into mixer and stir them 2-3 minutes.

**Note:** If the mortar castable can meet your construction requirements, less water, higher cold crushing strength.

2. The best temperature for the construction is between 5-20°C, the added water must be clean (pollution free), if the temperature of the water is below 5°C, you'd better heat it.

3. As per construction process, just to be sure take proper quantity materials each time in the mixer.

4. Put the material to where you want to use by ramming, casting or vibrating. After construction, the materials should be naturally curing for 3 days. After mixing let the paste sit and rest for 24 hours without applying. Following this 24 hours, start application. The mix cannot be exposed to the sun or high ambient temperature as this would cause rapid loss of moisture. Before doing a complete batch, it is suggested you apply the instructions to a small amount and check workability of the mix powder / water ratio you have applied.