

Fire Protection & Insulation Solutions

20 Dobra Road Yangebup, WA 6164 Ph: +61 8 9418 8826 Mobile: +61 402 002 359 sales2@darco.com.au Email:

TECHNICAL DATA SHEET

Sewing Thread Style KEV/SS/THREAD2/BLACK **Description and Advantages**

Darco style **KEV/SS/THREAD2/BLACK** is a high performance sewing thread made from a special steel core with 8 steel wires wrapped with a para-aramid cover. It has been designed as a sewing thread for a broad range of technical textiles offering a superior level of temperature resistance. The special steel core can withstand temperatures of approximately 300°C under mechanical strain and up to 500-600°C without any mechanical strain. It also provides good sewing performance, and is manufactured by the largest global thread supplier.



Heat and flame protective carpets, mats and

Flame retardant protective clothing

Main Uses:

- Welding blankets and • curtains
- Fire curtains
- Insulation jackets
- Thermal covers •

Technical Specification:

67% stainless steel wire AISI 316 L, 33% TWARON Material Construction 2100 Dtex Tex 210 Spool 420 gr Finish none Tensile strength 81 N Torsion Z350 Temperature 500-600°C continuous temperature without mechanical stress, 300°C continuous temperature with mechanical stress resistance 24 Needle Size

tarpaulins

Firefighter uniforms

^t Needle size recommendations are a guide only and ultimately depend on the sewing application.

Since conditions and applications vary considerably in the use of thread, the thread user should assure her or himself by preliminarily testing that the thread is suitable for the end use intended. Technical information listed above is based on current averages and should be taken only as indicative.

Additional Information:

Darco KEV/SS/THREAD2/BLACK sewing thread is suitable for use in heat and fire fighters' protective clothing according to EN ISO 11612, EN ISO14116 and EN 469. They are not suitable for use in protective clothing for electricians and welders as the relatively low vertical resistance (< 105_) material cannot guarantee protection from the possibility of electrical shock by contact with live electric conductors.